

Solder paste PW231-STV-GQ COSMO

Product description

GENMA SMD solder paste – our PW231-STV-GQ COSMO solder paste convinces with its higher tensile strength of the solder connections compared to SAC 305 while the costs are reduced. Due to its broad melting temperature range, this solder paste has an excellent anti-tombstone effect perfectly suited for vapor phase soldering. PW231-STV-GQ features an outstanding printability, long tackiness on the stencil, little residues after soldering, and excellent wetting properties. BGAs and difficult surfaces are soldered reliably. The solder paste can be soldered under air or nitrogen reflow. Cleaning is not necessary.

Technical properties

	Specific value	Testing method
Alloy	Sn 95,5 / Ag 1 / Bi 3 / Cu 0,5	
Melting temperature range	207 - 223	IEC61189-11
Powder size (µm)	22 - 38, type 4	IPC-TM-650-2.2.14.2
Viscosity (Pa · s)	200 ± 20	IPC-TM-650-2.4.34.3
Flux content (wt %)	11,8 ± 0,5	IPC-TM-650-2.3.34.1
Flux type	ROL1, no clean	IPC-J-STD-004B
Printing pitch (mm)	0,4	
Halide content (wt %)	0,06 ± 0,02	IPC-TM-650-2.3.35
Slump in print (mm)	≤ 0,2	IPC-TM-650-2.4.35
Slump in heat (mm)	≤ 0,3	IPC-TM-650-2.4.35 (180°C / 60sec)
Insulation resistance (Ω)	≥ 1 x 10 ¹¹ (40°C 90 % r. L)	IPC-TM-650-2.6.3.3
Insulation resistance (Ω)	≥ 5 x 10 ⁸ (85°C 85 % r. L)	IPC-TM-650-2.6.3.3
Migration test	No migration	IPC-TM-650-2.6.14.1
Copper mirror test	No corrosion	IPC-TM-650-2.3.32
Packaging	Jar (0,5 kg) Semco cartridge (0,65 kg, 1,2 kg)	
Shelf life	12 month at 0-10°C, 3 month at < 35°C	
Transport	Without cooling	
Tempering the solder paste	Set to room temperature before opening to avoid condensation.	
Recommended printing speed (mm/s)	20 - 80	
Recommended temperature during print (°C)	25 ± 3	
Recommended relative humidity in % during print	50 ± 20	


Compliance

Conform with RoHS-Regulation 2011/65/EU and 2015/863/EU

Contains no substances more than threshold (0,1%) according to REACH legislation EG Nr. 1907/2006 (SVHC list 1 - 30.05.2023)

Recommended Reflow Profile

Temperature (°C)



Preheating

The temperature increase should be 1°C to 10°C/sec until the preheating zone is reached.

To achieve a temperature spread (Δt) on the circuit board that is as limited as possible, the temperature in the preheating zone should be between 150 and 190°C and the preheating time should be 60 to 120 seconds. If the temperature is too low or the preheating time too short, the temperature spread (Δt) on the circuit board will be too high. If the temperature is too high and the preheating time too long the activators will get lost which may lead to poor melting of the solder paste.

Reflow peak

We recommend keeping the temperature at 220°C for 30 to 150 seconds, if possible. If this is impossible, a temperature of up to 250°C can be maintained for a shorter period of time. It must be ensured, however, that the components are suited for the higher temperature.

Cooling down

The cooling rate should be between 5 and 10°C/sec. If the cooling rate is too low components may be displaced or come up and reduce the strength of the solder connections. If the cooling rate is too high, however, components can be damaged through thermal shock.