Solder paste NP303-FLV-1B-T4

Product description

GENMA solder paste - our NP303-FLV-1B-T4 solder paste was developed for use in vacuum soldering systems. The flux in our NP303-FLV-1B-T4 dissolves without leaving any residue. DIE bonding can be carried out directly after soldering without cleaning on a 100% process-safe surface. The solder paste leaves a clean surface without residues after the soldering process in the vacuum reflow oven. This increases process reliability enormously, saves process costs and shortens the throughput times of the product in the production process. In combination with the necessary vacuum soldering system, the solder joints are virtually free of voids. The solder paste is primarily used in DIE attach and power device packaging applications. The residue-free and void-free solder joint ensure good current and heat transfer in power electronics. When soldering DIE with DCB / DBC (direct copper bonded), high layer thicknesses are often required. The solder paste is designed for the special requirements of the printing process and can be modified to meet customer-specific requirements. Up to now, preforms or solder pastes with classic flux have mostly been used in these applications. When using preforms, a preform must be purchased for each geometry. Solder paste printing is much more flexible here and can replace the high variance of preforms. When switching from resin-containing solder pastes to our NP303-FLV-1B-T4, the entire cleaning process, including surface inspection, can be eliminated. This increases process reliability, saves costs, reduces throughput times and unnecessary emissions.

Technical properties

	Specific value	Testing method
Alloy	Sn 96,5 / Ag 3,0 / Cu 0,5 / SAC305	
Melting temperature range	217 - 221	IEC61189-11
Powder size (µm)	22 - 38, type 4	IPC-TM-650-2.2.14.2
Packaging	Jar (0,5 kg) Semco cartridge (0,65 kg, 1,2 kg)	
Tempering the solder paste	Set to room temperature before opening to avoid condensation.	
Recommended printing speed (mm/s)	20 - 80	
Recommended temperature during print (°C)	25 ± 3	
Recommended relative humidity in % during print	50 ± 20	
Squeegee material	Metal, polyurethane, plastic (hardness 70 - 100 Shore)	
Squeegee anglel (°)	40 - 70	
Clearance (mm)	0 - 0,1	
Stencil separation speed (mm/sec)	3 - 11	
Solder paste roll size (mm)	15 - 25	

Compliance

Dated 13.11.2025

Conform with RoHS-Regulation 2011/65/EU and 2015/863/EU.

Contains no substances (SVHC-list) more than threshold (0,1%) according to REACH legislation EG Nr. 1907/2006.

GENMA Europe GmbH | Robert-Bosch-Str. 18 | 71394 Kernen i. R. Germany | Phone +49 7151 206610 | team@genma.eu | www.genma.eu

Contains no substances as defined by the Toxic Substance Control Act (TSCA) of the United States Environmental Protection Agency.

Contains no substances according to POP Regulation EU 2019/1021.

Contains no Per- and PolyFuluoroAlkyl Substances (PFAS).

Contains no phthalates or latex.

Contains no substances according to California Proposition 65.

Recommended Reflow Profile



Preheating

Empfohlener Restsauerstoffgehalt <500ppm in der Vorheiz- und Peakzone. Im Falle, dass einzelne Angaben nicht erfüllt werden können und daraus resultierend das Lötergebnis nicht zufriedenstellend ist, empfiehlt es sich den Restsauerstoffgehalt weiter abzusenken.

Der Temperaturanstieg bis zur Vorheizzone (100°C) sollte <2°C / Sekunde betragen. Ein zu schneller Temperaturanstieg kann zum Verlaufen der Lötpaste führen.

Um eine möglichst kleine Temperaturstreuung (⊿t) auf der Leiterplatte zu erreichen, sollte die Temperatur in der Vorheizzone 100 – 170°C und die Vorheizzeit 40 – 70 Sekunden betragen. Im Falle einer niedrigeren Temperatur und kürzerer Zeit ist die Temperaturstreuung (⊿t) auf der Leiterplatte zu groß. Bei zu hoher Temperatur und längerer Zeit gehen die Aktivatoren verloren, was dazu führen kann, dass die Lötpaste nicht aufschmilzt.

Im Bereich von 170°C bis 220°C wird ein Anstieg von 4°C empfohlen. Im Falle eines langsameren Temperaturanstieges kann der Aktivator im Flussmittel verloren gehen, was dazu führt, dass die Lötpaste nicht schmilzt.

Reflow peak

Wir empfehlen, die Temperatur möglichst 30 – 90 Sekunden über 220°C zu halten. In der Spitze sollten Temperaturen von 250 - 270°C erreicht werden. Dabei sollte sichergestellt sein, dass die Bauteile für die hohe Temperatur geeignet sind. Empfohlenes Vakuum <10kPA. Eine zu niedrige Temperatur und/oder ein zu schwaches Vakuum können dazu führen, dass Voids und/oder Rückstände vom Flussmittel auf der Lötstelle verbleiben.

Cooling down

Die Abkühlgeschwindigkeit sollte <10°C / Sekunde betragen. Zu langsames Abkühlen kann dazu führen, dass sich Bauteile verschieben oder aufstellen und die Stärke der Lötverbindungen schwächen. Zu schnelles Abkühlen dagegen kann Bauteile durch thermischen Schock beschädigen.

GENMA Europe GmbH | Robert-Bosch-Str. 18 | 71394 Kernen i. R. Germany | Phone +49 7151 206610 | team@genma.eu | www.genma.eu